



## MONOLITHICS

BRAND	MgO %	CaO %	Cr <sub>2</sub> O <sub>3</sub> %	SiO <sub>2</sub> %	Fe <sub>2</sub> O <sub>3</sub> %	Al <sub>2</sub> O <sub>3</sub> %	LOI	Grading (mm)	Service Temp. °C	Density (gm/cc)	
										Loose	Vibrating
SUPERFET 45	48	47	-	2.50	6.50	1.00	1.5	0-4	1700	2	2.20
SUPERFET 70	65	16	-	5.00	3.00	2.00	2	0-7	1750	2	2.25
SUPERHEARTH - 25	68	27	3.0	1.25	4.50	0.80	1	0-8	1800	2.30	2.35
SUPERHEARTH	77	20	-	1.00	1.00	0.75	1	0-5	1850	2.35	2.40
SUPERGUN II	80	4	-	4.00	1.00	1.00	-	0-3	1750	2.30	-
SUPERGUN II C	84	2	3	3.00	1.00	1.00	1	0-3	1750	2.50	-
MAGRAM 84	83	-	-	9.00	-	-	-	0-5	1750	2.45	-
MAGRAM 95	94	1.25	1.5	1.25	0.70	-	-	0-5	1750	2.50	-
MAGFILL EF	88	2	-	4.50	1.00	1.00	7	3-8	1750	-	-
OLIFILL EF	45	2	-	35.00	8.50	1.00	-	0-6	1750	-	-